

# TECHNICAL DATA SHEET

## INK

issued: August 1, 2016



AAKASH CHEMICALS

THE SKY  
IS THE LIMIT

# Finawax O

Slip agent  
(Oleamide)

CAS No. 301-02-0

EINECS # 206-103-9

### PHYSICAL PROPERTIES

Density g/cm <sup>3</sup>	0.97
Melting Point	73°C +/-5 / 163°F +/-9
Flash Point	204°C / 400°F
Boiling Point	260°C / 500°F
Acid Value	1.0 Maximum
Iodine Value	80 - 95
Amine Purity %	98 - 100
Solubility in Water	Insoluble
Moisture Content %	0.25 Maximum
Gardner Color	2.0 Maximum
Bio Based Content	Vegetable






### FASTNESS PROPERTIES

Warpage None



### PARTICLE SIZE

Micronized 60-100 µm  
Microbeads 400-600 µm  
Beads 800-1200 µm  
Pellets Small - 2.0 mm  
Pellets Large 2.2 mm

### APPLICATION PROFILE

Solvent Flexo	Water Flexo	Offset	Screen	Gravure	UV
					

### LEGEND

 recommended  
 partially recommended

### Disclaimer:

The above information is based on the data of which we are aware and is believed to be correct as of the data hereof. Since this information may be applied under conditions beyond our control and with which we may be unfamiliar and since data made available subsequent to the date hereof may suggest modifications of the information, we assume no obligation, express or implied, or liability for the use obligation, express or implied, or liability for the use of or reliance on the information and data provided. The information is furnished upon condition that the person receiving it shall make their own determination of the suitability of the material for their particular purpose.

AAKASH CHEMICALS  
AND DYE-STUFFS, INC.

THE SKY  
IS THE LIMIT

info@akashchemicals.com  
www.akashchemicals.com

Ph: 630-469-3838  
TF: 800-255-4855  
Fax: 630-469-2255  
561 MITCHELL RD.  
GLENDALE HEIGHTS, IL 60139