# TECHNICAL DATA SHEET COATINGS

issued: August 1, 2016



# Akafast Yellow F2G 🍐

Medium yellow with good solvent fastness and lightfastness (Benzimidazolone)

7

Pigment Yellow 194 CAS No. 82199-12-0 CICN No. 11785 EINECS # 279-914-9

PHYSICAL PROPERTIES

1.46

### **FASTNESS PROPERTIES**

Heat Stability Mass °C

Light Stability Mass

acid 5 alkali 5 MEK 4

xylene

**FASTNESS PROPERTIES** 

3

pH 5-7 Oil Absorption % 90-100

Density g/cm<sup>3</sup>

**INDUSTRY PROFILE** 

Automotive	Architectural	Industrial	Coil	Powder

### **LEGEND**

recommended

♦ partially recommended

## Disclaimer:

The above information is based on the data of which we are aware and is believed to be correct as of the data hereof. Since this information may be applied under conditions beyond our control and with which we may be unfamiliar and since data made available subsequent to the date hereof may suggest modifications of the information, we assume no obligation, express or implied, or liability for the use of or reliance on the information and data provided. The information is furnished upon condition that the person receiving it shall make their own determination of the suitability of the material for their particular purpose.