TECHNICAL DATA SHEET COATINGS

issued: March 21, 2018



Akahue Yellow 2GXI 🍐

Green shade, semi-opaque yellow with good overall fastness & flow properties (Monoazo)

Pigment Yellow 74 CAS No. 6358-31-2 CICN No. 11741 EINECS # 228-768-4

PHYSICAL PROPERTIES

FASTNESS PROPERTIES

FASTNESS PROPERTIES

 Density g/cm³
 1.30

 pH
 6-8

 Oil Absorption %
 35-65

Heat Stability Mass °C 150
Heat Stability Tint °C 180
Light Stability Mass 7
Light Stability Tint 5

acid 4-5 alkali 4-5 MEK 4 xylene 4

INDUSTRY PROFILE

Automotive	Architectural	Industrial	Coil	Powder
	\(\)			

LEGEND

recommended

♦ partially recommended

Disclaimer:

The above information is based on the data of which we are aware and is believed to be correct as of the data hereof. Since this information may be applied under conditions beyond our control and with which we may be unfamiliar and since data made available subsequent to the date hereof may suggest modifications of the information, we assume no obligation, express or implied, or liability for the use of or reliance on the information and data provided. The information is furnished upon condition that the person receiving it shall make their own determination of the suitability of the material for their particular purpose.